

TPU

Product features:

- Best grade material, sticks easily to print bed and excellent layer adhesion.
- 1.75mm Filament Diameter (Dimensional Accuracy +/- 3% of diameter).
- Vacuumed Sealed with Desiccant and box packed.
- Recommended Extrusion/Nozzle Temperature 220°C - 240°C and Heated bed 50°C -30°C.

Technical Data:

Property, Test Condition	Standard (ASTM)	Unit	values
Shore Hardness	D2240	Shore A	90
Tensile Strength,	D638	psi (MPa)	18
Elongation at Break	D638	%	530
Specific gravity	D D792	g/cc	1.21

CURRENT AVAILABILITY OF COLOURS:



WHITE